

GENERAL PRODUCT DESCRIPTION

Capa[®] 2161A is a premium grade linear polyester diol derived from caprolactone, terminated by primary hydroxyl groups. It has a molecular weight of 1600 and a typical OH value of 70 mg KOH/g.

The product has been specially developed as an intermediate for the production of high quality polyurethane elastomers, where outstanding resistance to hydrolysis is required. It is also recommended for the production of high quality polyurethane coatings and fibres.

TYPICAL PROPERTIES

Physical Form	White waxy solid
Mean Molecular Weight	1600
Melting Point	35°C - 50°C
Hydroxyl Value	70 mg KOH/g
Acid Value	<0.05 mg KOH/g
Water Content	<0.02%
Viscosity at 60°C	300 mPa.s

DENSITIES

The typical specific gravity (SG) of the material, measured at 55°C c.f. water at 20°C, is 1.071.

SOLUBILITY PARAMETERS

The solubility parameter (δ) is 9.34 – 9.43 (cal/cm³)^{1/2}.

HANDLING AND STORAGE

Capa[®] 2161A is supplied in lacquered mild steel drums containing 200 kg net. The product should continue to be stored in air-tight containers to prevent moisture pick-up from the atmosphere.

For further information please contact:

Perstorp UK Limited
Baronet Road
Warrington, Cheshire WA4 6HA
United Kingdom
Tel. +44 (0)1925 643500
Fax. +44 (0)1925 232207
contact.capa@perstorp.com
www.perstorpcaprolactones.com

Perstorp Specialty Chemicals AB
SE-284 80 Perstorp,
Sweden
Tel. +46 435 38000
Fax +46 435 37067
technical.support@perstorp.com
www.perstorp.com